

Technical information (05/22)

## **MOBIHEL CC TINTERS**

- · For deep and saturated shades
- Intense shine
- Brilliant appearance
- Packaging à 100 ml
- Colour: 7 different shades

SUBSTRATE	MOBIHEL 2K FILLER MOBIHEL BASE / HYDRO	
	to cover to cover 2 layers	

	Application with spray gun:	1,2 - 1,3 mm 2 - 2,5 bar
	Number of layers:	2
	Film thickness:	50 - 60 μm
	Flash-off:	10 - 15 min/20°C between layers 10 - 15 min/20°C before drying in oven
	Drying time at 20°C: Drying time at 60°C:	16 h 30 min. (object temperature)
R	Drying time (infra-red short- wave):	8 - 12 min. Distance to the object: 70 - 80 cm
201	Shelf life:	2 years

2K materials react with humidity; take care that all containers and tools are absolutely dry. While coating, the ambient relative humidity should not exceed 80%.

Helios TBLUS d.o.o., Količevo 65, 1230 Domžale Slovenia T: + 386 1 722 40 00, E: office@helios-refinish.com, www.helios-refinish.com







FOR PROFESSIONAL USE ONLY - See Safety Data Sheet

Close the packaging of the Hardener immediately after use, because the product reacts with air humidity and may cause defects in the product. The data may vary under various conditions.

Any part of this information may change at any time without notice.

The information was derived from years of experience in the collaboration of Development and Technical Services and is the property of HELIOS Refinish.

We guarantee that the quality of work carried out according to our instructions delivers results while we disclaim any liability if any other products were used or if other factors influenced the final appearance.

The latest version of TDS supersedes all previous versions. You can obtain the latest version from general distributor in your country. The user of this product should use the product in accordance with the laws and regulations for safety at work and waste management.

Version: 2022-20 (10.05.2022)



