

Aluminium-reinforced putty finish - 1.8kg MAE1.8

v.02-04-2012

Features :

This aluminum-reinforced putty finish boasts good shaping properties and is very easy to sand with P150 abrasive to eliminate transitions between the filler and the surface being worked. This filler has excellent temperature resistance. Ideal for filling dents and other imperfections. Suitable for hand or machine sanding. It adheres very well to the surface; it is not necessary to use a finishing filler after this filler.

Application:

Before applying the sealant, the surface must be clean, degreased, dry, and matte. Stir the sealant thoroughly and add 2-3% of the appropriate hardener. If the temperature is too high, the service life may be reduced and the drying time may be accelerated.

Note : Using too much hardener may cause discoloration of the top coat. Therefore, it is not recommended to use the sealant below 15°C.

Technical data :

VOC content : 2004/42/II B(b)(250) <250

Shelf life : 12 months Density: 1,78 g/cm³ Color : metallic



Cleaning

Aluminium-reinforced putty 100 g



Hardener addition

BPO hardener 2-3 g



Body filling

3 - 5 min.



Drying time

16 - 30 min.



Hand sanding/dry

P150 - P320



Machine sanding/dry

P150 - P320



Store in cold place