

CARFINISH



AUTOMOTIVE



smartBODYFILLER

FIBER POWER XTRA

Fiber reinforced
premium putty

FIBER POWER XTRA



Maximum strenght

Extra short high-tech fibers

Smooth and easy application

Easy to sand

DI 00 46455 1 – 1,2 kg

Fiber Power Xtra, our new fiber reinforced premium putty which can be applied on multiple surfaces, delivering a maximum strenght and adhesion.

The increased amount of premium micro filling components and the extra short fibers produces an even more soft and smooth finish than ever before.

This new concept, including premium filling parts, high-end resin and extra short fibers makes Fiber Power Xtra very easy to sand and delivers you a ready to prime surface.

*Test it yourself and experience
the many advantages it brings
to your repair process!*

TECHNICAL DATA SHEET

FIBER POWER XTRA

Fiber reinforced premium putty

Edition date: 08.2021 | Page 1/1

DESCRIPTION	FOR PROFESSIONAL USE ONLY Fiber Power Xtra fiber reinforced polyester filler for the repair and filling of body parts such as fenders, front aprons, engine bays, spoilers and side skirts.												
SUBSTRATES	Excellent adhesion on bare metal, sheet steel, aluminium, galvanized metal or polyester surfaces. Epoxyprimer recommended for best protection. Do not use it on thermoplastic surfaces or on top of any so called Wash-Primers or Acid-Primers.												
PREPARATION	Identify the type of substrate before you apply a coating with Fiber Power Xtra. Before sanding, thoroughly clean the area to be repaired removing all traces of dirt, oil and wax residues. Lightly abrade the repair area to key the surface. Use a fine abrasive to remove any deep or heavy scratch pattern. Remove the dust. The area to be repaired must be completely dry before application of product.												
MIXING	The mixing ratio is 2-3 % by weight. Place the required amount of hardener on a clean, grease free, mixing board and add the requisite 2-3 % hardener. Thoroughly mix the material to a consistent, homogenous mass that is one uniform colour. Only use the CarFinish hardener provided.												
APPLICATION	First, apply a very thin layer of mixed material with firm pressure to the repair area. This promotes an optimum, pin-hole free application and excellent adhesion. Increase to the desired depth of repair by applying layers of product. Do not apply over fresh or not fully cured coated surfaces. Before finishing allow to cure fully.												
SANDING	After 15 minutes the sanding process can begin. The initial surface can be sanded with P80 grit moving through up to a P240 grit.												
TECHNICAL DATA	<table border="1"><tr><td>Colour</td><td>light green</td></tr><tr><td>Physical state</td><td>creamy/liquid</td></tr><tr><td>Working time</td><td>4-5 minutes at 20 °C</td></tr><tr><td>Dry to sand time</td><td>15-20 minutes</td></tr><tr><td>Ingredients and precautions</td><td>Safety data sheet (MSDS) available on request</td></tr><tr><td>VOC</td><td>EU limit for volatile organic compounds: 250 g/l (2007) This product contains max 6 g/l VOC.</td></tr></table>	Colour	light green	Physical state	creamy/liquid	Working time	4-5 minutes at 20 °C	Dry to sand time	15-20 minutes	Ingredients and precautions	Safety data sheet (MSDS) available on request	VOC	EU limit for volatile organic compounds: 250 g/l (2007) This product contains max 6 g/l VOC.
Colour	light green												
Physical state	creamy/liquid												
Working time	4-5 minutes at 20 °C												
Dry to sand time	15-20 minutes												
Ingredients and precautions	Safety data sheet (MSDS) available on request												
VOC	EU limit for volatile organic compounds: 250 g/l (2007) This product contains max 6 g/l VOC.												
STABILITY	Best before date: Fiber Power Xtra minimum shelf life with closed tin: 12 months Hardener: 18 months												
STORAGE	According to the requirements of local regulations. Observe the precautionary statements given on the label. Storage temperature +5°C to +30° C. Store in a cool, well-ventilated place away from incompatible materials and sources of ignition. Keep away from oxidising agents, strong alkalis and acids. Smoking is prohibited in the immediate vicinity. Prevent unauthorized access. Opened containers should be closed carefully and tightly. Keep upright to prevent leakage. Do not empty into drains. Do not return mixed material to the original container.												
SAFETY INSTRUCTIONS	Be sure to read all instructions and warnings before using CarFinish products. Safety data sheets for all materials are available online at www.carfinish.eu .												

DI 00 46455 1 – 1,2 kg

Your CarFinish partner:

SISTEC Coatings GmbH

Mauserstraße 6/1
71640 Ludwigsburg
Germany

T +49 (0)7141 9905516
info@carfinish.eu
www.carfinish.eu