

90 Line Glasurit® Basecoat

G / T

- Application:** Metallic and solid-colour basecoat/clearcoat finishing. Wet-on-wet process with Glasurit 923- Clear.
- Properties:** Very good hiding power, high efficiency.
Water-thinnable, less than 10% organic solvents.
- Remarks:**
- Mixing formulas with 90-M4 and mixing bases are available to cover the whole range of colours needed in automotive refinishing.
 - At rather high temperatures or when refinishing large surfaces, it is possible to replace 90-M4 by 90-M4 slow, while replacing 93-E3 Adjusting base by 93-E3 slow at the same time.
 - Mixtures will keep for up to 6 months when stored in plastic containers or cans coated inside.
 - Use of 93-IC 330 if recommended by car manufacturers (see Technical Information).
 - Flash-off times can be reduced significantly by using appropriate air blow equipment.
 - Flash-off time before application of 923- Clear: 2-3 min. (until surface is mat).
 - When using white colors with high spray viscosity the mixing ratio can be changed to 100 : 80.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.










2004/42/II B(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 419 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



90 Line Glasurit® Basecoat

G / T

	Paint system	RATIO Aqua	
		Spreading rate:	130 m ² /l at 1 µm
	Mixing ratio	2 : 1 100% by vol. 90 Line Metallics/Solids (acc. to mixing formula)	
	Reducer	50% by vol. 93-E3 Adjusting Base * (stir IMMEDIATELY after having added adjusting base)	
		*When using 90-M4 slow in the mixing formula, 93-E3 slow must also be used.	
	Spray viscosity DIN 4 at 20°C	approx. 18-24 s	
	Gravity cup Spraying pressure	HVLP gun: 1.3 mm 2.0-3.0 bar / 0.7 bar at the nozzle	Compliant gravity-feed gun 1.3-1.4 mm, 2.0 bar
	Number of spraycoats	2 (spray to cover) + ½ to match the effect	Film thickness: 10-15 µm
	Flash-off at 20°C	Approx. 5 min. after each spraycoat.	
	Intermediate drying Drying at 20°C Blow dry with Dry Jet	Flash off until mat after each spraycoat.	
	Sanding	Remove dust nibs by dry sanding; gently fade out applying mist coat afterwards.	

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 419 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

